



ARCHER RUBBER LLC  
 213 CENTRAL STREET  
 MILFORD, MA 01757-3458  
 TEL: (508) 473-1870  
 FAX: (508) 478-7078  
[www.archerrubber.com](http://www.archerrubber.com)  
[sales@archerrubber.com](mailto:sales@archerrubber.com)

*Engineered Coated Fabrics*

STYLE# 7100

DESCRIPTION / CONSTRUCTION

DOUBLE COATED HYPALON ON NYLON

AREAS OF APPLICATIONS

BELTING MATERIAL

CHARACTERISTICS / PHYSICAL PROPERTIES

TEST / METHOD	Federal Standard 191A or ASTM	REQUIREMENT
FINISHED WIDTH (MIN. USABLE)		60
FINISHED WEIGHT (OZ./YD <sup>2</sup> MAX)	Fed. Std. 191A METHOD 5041	16.0 TO 18.0
BREAKING STRENGTH (LBS. MIN "GRAB")	Fed. Std. 191A METHOD 5100	WARP 350 FILL 300
TEARING STRENGTH (LBS MIN)	Fed. Std. 191A METHOD 5136	WARP 40 FILL 30
COATING ADHESION (LBS/2 INCHES MIN)	Fed. Std. 191A METHOD 5970	8.0
TEMPERATURE RANGE (MIN. TO MAX.)		-20° F to 200° F

*The information contained herein was developed in our laboratories and is believed reliable. It is offered in good faith. However, as prospective users conditions and methods of use are beyond our control, we recommend the user determine the suitability of this product before adapting our materials on a commercial scale.*