



ARCHER RUBBER CO.  
CHEM-TECH RUBBER CO.  
213 CENTRAL STREET  
MILFORD, MA 01757-3458  
TEL: (508) 473-1870  
FAX: (508) 478-7078  
www.archerrc.com  
archerrc@ma.rcn.com

2236

#### DESCRIPTION / CONSTRUCTION

D/C Marron Nitrile on Cotton

#### AREAS OF APPLICATIONS

##### ELECTRICAL BLANKETS

Class 00 maximum use 500 VAC

#### CHARACTERISTICS / PHYSICAL PROPERTIES

TEST / METHOD	Method Used	REQUIREMENT
Finished Weight (Oz./Sq.Yd. min. to max.)	ASTM-D-751	23.0 to 29.0
Finished Gauge (Inches)	ASTM-D-1777	0.023 to 0.027
Finished width (Min.usable inches)	ASTM-D-3774	36
Mullen Burst (PSI Min.)	ASTM-D-3786	70
Coating Adhesions (Lbs./inch min.)	ASTM-D-751	No Requirement
Breaking Strength (Lbs./inch min.)	ASTM-D-5034	Warp 75 Fill 75
Temperature Range		-20 <sup>o</sup> F to 200 <sup>o</sup> F

The information contained herein was developed in our laboratories and is believed reliable. It is offered in good faith. However, as prospective users conditions and methods of use are beyond our control, we recommend the user determine the suitability of this product before adapting our materials on a commercial scale.